

A

PTO/SB/05 (4/98)
Approved for use through 09/30/2000 OMB 0651-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE
collection of information unless it displays a valid OMB control number

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

Attorney Docket No.	BEIERSDORF 606-WCG
First Inventor or Application Identifier	Detlef GROTH
Title	[See "Appendix"]
Express Mail Label No.	EE473057642US

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

ADDRESS TO:

See MPEP chapter 600 concerning utility patent application contents.

Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

1. ☒ * Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
2. ☒ Specification [Total Pages 8]
(preferred arrangement set forth below)
- Descriptive title of the Invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☒ Drawing(s) (35 U.S.C. 113) [Total Sheets 2]
4. Oath or Declaration [Total Pages]
- a. ☐ Newly executed (original or copy)
 - b. ☐ Copy from a prior application (37 C.F.R. § 1.101)
(for continuation/divisional with Box 16 completed)
 - i. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application
see 37 C.F.R. §§ 1.63(d)(2) and 1.33(c)

5. ☐ Microfiche Computer Program (*Appendix*)
6. Nucleotide and/or Amino Acid Sequence Submission
(*if applicable, all necessary*)
- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. ☒ Assignment Papers (cover sheet & document(s))
8. ☐ 37 C.F.R. § 3.73(b) Statement ☐ Power of Attorney
(when there is an assignee)
9. ☐ English Translation Document (if applicable)
10. ☐ Information Disclosure Statement (IDS)/PTO-1449 ☐ Copies of IDS Citations
11. ☒ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
13. ☐ * Small Entity Statement(s) ☐ Statement filed in prior application, Status still proper and desired
(PTO/SB/09-12)
14. ☒ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
15. ☐ Other:

* NOTE FOR ITEMS 1 & 13: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C.F.R. § 1.28).

16. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:
- | | | | |
|---------------------------------------|-------------------------------------|---|--|
| <input type="checkbox"/> Continuation | <input type="checkbox"/> Divisional | <input type="checkbox"/> Continuation-in-part (CIP) | of prior application No. _____ / _____ |
|---------------------------------------|-------------------------------------|---|--|

Prior application information: Examiner _____ Group / Art Unit: _____
For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.


17. CORRESPONDENCE ADDRESS

☐ Customer Number or Bar Code Label

or ☒ Correspondence address below

(Insert Customer No. or Attach bar code label here)

Name	William C. Gerstenzang				
	NORRIS, McLAUGHLIN & MARCUS, P.A.				
Address	660 White Plains Road				
City	Tarrytown	State	New York	Zip Code	10591
Country	U.S.A.	Telephone	914-332-1700	Fax	914-332-1844

Name (Print/Type)	William C. Gerstenzang	Registration No. (Attorney/Agent)	27,552
Signature		Date	Feb. 2, 2000

Burden Hour Statement This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231

Attorney Docket No. : Beiersdorf 606-WCG
: 6713-St-bb

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant(s) : Detlef GROTH, Arne KOOPS, Axel BURMEISTER, Jochen STÄHR
Serial No. : To Be Assigned
Filed : Herewith
For : ANTICOUNTERFEIT, LASER-MARKABLE LABEL PRODUCED BY
DIFFRACTION GRATINGS
Art Unit : To Be Assigned
Examiner : To Be Assigned

February 2, 2000

BOX PATENT APPLICATIONS
Hon. Assistant Commissioner
for Patents
Washington, D. C. 20231

PRELIMINARY AMENDMENT

Sir:

Prior to examination, please amend the above-identified application as follows:

IN THE ABSTRACT

Please cancel the abstract and substitute the abstract annexed as a separate page
hereto.

IN THE CLAIMS

Claim 2 (amended). Process according to Claim 1, [characterized in that]

wherein the support foil [consists of] is a permanently embossed thermoset or thermoplastic material.

Claim 3 (amended). Process according to [Claims 1 and 2, characterized in that] Claim 1, wherein the support foil [consists of] is a polyester or polyamide.

Claim 4 (amended). Process according to [Claims 1 to 3, characterized in that] Claim 1, wherein the sheet is extruded, coated or cast onto the support foil.

Claim 5 (amended). Process according to [Claims 1 to 4, characterized in that] Claim 1, wherein the sheet [consists of] is a coating film [which in particular is subsequently] and is subjected to electron beam curing.

Claim 6 (amended). Process according to Claim 5, [characterized in that] wherein the coating film has a thickness of from 0.5 to 30 μm [, in particular from 5 to 15 μm].

Claim 7 (amended). Process according to [Claims 1 to 6, characterized in that] Claim 1, wherein an additional adhesive layer of from 5 to 70 μm in thickness is arranged on the sheet and, [if required] optionally, a release paper is arranged on [this] said adhesive layer.

Claim 8 (amended). A [S]heet [obtainable by a process according to at least one of the preceding claims] prepared according to the process of Claim 1.

REMARKS

This preliminary amendment is being filed to conform the claims and abstract to conventional format, and to eliminate multiple dependency.


Favorable action is respectfully solicited.

ADDITIONAL FEE

Please charge any insufficiency of fees, or credit any excess, to Deposit Account No. 14-1263.

Respectfully submitted,

NORRIS, McLAUGHLIN & MARCUS, P.A.

By 
William C. Gerstenzang
Reg. No. 27,552

WCG:kts

660 White Plains Road
Tarrytown, New York 10591-5144
(914) 332-1700

ABSTRACT

Process for producing an anticounterfeit label having a holographic image, and labels produced according to the process.

032020-1636360

APPENDIX

BEIERSDORF 606-WCG

TITLE:

ANTICOUNTERFEIT, LASER-MARKABLE LABEL PRODUCED BY DIFFRACTION GRATINGS

LIST OF INVENTORS:

1. Detlef GROTH
2. Arne KOOPS
3. Axel BURMEISTER
4. Jochen STÄHR

"Express Mail" Mailing Label No. EE473057642US

Date of Deposit: February 2, 2000

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.

NORRIS, McLAUGHLIN & MARCUS, P.A.

By: 

Description

Anticounterfeit, laser-markable label produced by diffraction gratings

5 The invention relates to a process, and to its resultant products, for producing an anticounterfeit label which bears an optically active image produced by means of diffractive structures.

10 Since technically it is very complex to copy holograms, they are nowadays used, for example, on the widespread chipcards (ec card) and banknotes.

The known processes for producing labels with diffraction gratings and holograms are very complex and costly.

15 Primarily, diffractive or holographic structures are transferred by means of an embossing process (for example Holosecure with shim) or printing process (for example Holoprint) to a sheet backing, and in a subsequent step are rendered visible by the application of a metallic film.

20 One way of transferring the holographic metallic film to the backing material (for example concert tickets, banknotes) is by means of a hot embossing process. A disadvantage of these labels is that they possess a high level of susceptibility to mechanical and environmental effects. Under conditions of normal use, they may lose their optical properties, and so it cannot be ascertained whether the loss is an
25 indication of counterfeiting or of copious usage.

For this reason, labels with a protective laminate are used in order to counter these disadvantages.

30 Hologram sheets of this kind have the following structure:

- Backing sheet made, for example, of polyethylene terephthalate (PET) with a thickness of preferably 12 μm , to which a structured coating film is applied

- Metal film of from 1 to 10 nm (for example, vapour-coated aluminium)
- Adhesive layer with a preferred thickness of between 10 and 25 μm .

5 This multilayer structure fulfils its purpose, since the resulting product is mechanically more resistant.

Nevertheless, this structure has a tendency for the individual layers to separate - that is, a tendency towards delamination - and so, as a result of the destruction brought about through usage, the identification of authenticity is no longer possible.

10 All of these methods are applied to the surface and therefore can be used only in an extremely limited manner if at all for the known laser labels which are used, for example, for identification plates, since then the extremely resistant surface of high optical quality is altered and impaired. Furthermore, the application of an additional layer as described above prevents markability and cutability by means of a NdYAG laser.

15 The object of the invention is to provide a process for producing a sheet having a hologram without the known disadvantages of the prior art.

20 This object is achieved by means of a process as set out in accordance with Claim 1. The subclaims relate to particularly advantageous embodiments of the process and to a sheet having a hologram and obtainable by the process of the invention.

25 Accordingly, the invention provides a process for producing a sheet, in which first of all a support foil is embossed by means of an embossing tool, the embossing tool having holographic structures, and then a sheet is produced on the embossed support foil so that the structure is transferred to the sheet and results in at least one hologram.

30 Therefore, the side of the embossing tool facing the material to be embossed is shaped so as to give a structure which comprises a diffraction grating or a holographic image.

35 Since this hologram is produced in the sheet itself, there is no harmful multilayer structure and the diffraction grating produced in this way possesses the same resistance and laserability as the sheet itself.

In one advantageous embodiment the support foil consists of a permanently embossed thermoset or thermoplastic material, in particular polyester or polyamide.

The support foil preferably has a thickness of from 12 to 500 μm , in particular 50 μm .

5 The support foil can be provided with a very wide variety of motifs, examples being company logos or advertising. The embossing of the support foil produces a negative impression on the visible surface of the sheet of the invention.

The embossing of the support foil can be carried out, for example, in varying thickness and/or depth using a metal embossing die. The depth of embossing is dependent on the embossing pressure set, which acts on the magnetic cylinder used in the
10 embossing process, and counterpressure cylinder.

In a further advantageous embodiment, the sheet is extruded, coated or cast onto the support foil.

15 The sheet preferably consists of a coating film, which in particular is subsequently subjected to electron beam curing.

Four types of coating material can be used in principle for the object of the invention, provided that their stability is sufficient: for example, acid-curing alkyd-melamine
20 resins, addition-crosslinking polyurethanes, free-radically curing styrene coating materials, and the like. Particularly advantageous, however, are radiation-curing coating materials, since they cure very rapidly without laborious evaporation of solvents or the action of heat. Such coating materials have been described, for example, by A. Vrancken (Farbe und Lack 83, 3 (1977) 171).

25 Furthermore, the coating film preferably has a thickness of from 0.5 to 30 μm , in particular from 5 to 15 μm .

The coating film employed with preference is applied to the embossed support foil and
30 is cured under effectively oxygen-free conditions by the action of an electron beam of high energy (from 150 to 500 kV).

Furthermore, the coating film is preferably multilayer, and the layers consist of cured, i.e. crosslinked coating material: in particular, they comprise an upper coating film
35 which is from 1 to 20 μm thick, is applied without solvent and is cured by means of electron beams, and a lower coating film which is from 20 to 500 μm thick, is applied without solvent and is cured by means of electron beams.

In a further advantageous embodiment, an additional adhesive layer of from 5 to 70 μm , in particular from 10 to 30 μm , in thickness is arranged on the sheet and, if required, a release paper is arranged on this adhesive layer.

- 5 The third layer, comprising a pressure-sensitive adhesive, hot-melt adhesive or reactive adhesive or the like, is provided for bonding to a substrate.

Finally, the concept of the invention embraces a sheet obtainable by a process as described above.

10

The sheet produced in accordance with the process of the invention features a large number of advantages such as were not foreseeable for the person skilled in the art.

On the basis of the holograms, the sheet is rapidly identifiable, the holograms being visible optically but virtually intangible. Therefore, essentially no haptic impression is

15

produced. Using the sheet, the presentation of holograms even on a black substrate is possible for the first time.

20

The invention will be elucidated below with reference to two working examples, without being restricted thereto.

Figure 1 shows the embossing of the support foil and
Figure 2 shows the structure of the sheet of the invention.

- 25 According to Figure 2, the desired holograms are first of all embossed on a support foil 1 and comprise, for example, the company logo of the manufacturer of the sheet of the invention.

This is done using a roller 4 on which a metal embossing die 3 is fastened. The embossing die 3 has appropriate diffraction gratings.

30

The support foil 1 is guided along under the roller 4, which rotates in the direction of the arrow and is pressed onto the support foil 1 at a pressure of 500 to 2000 psi.

The support foil 1 carries the individual embossing lines 11, whose largest spacing A always has a width of less than 20 μm .

35

Figure 2 shows how a coating film 2 has been cast and distributed on the previously embossed support foil 1. In the coating film 2, this produces embossed patterns whose width B is substantially identical to the distance A.

- 5 Following the removal of the sheet from the support film 1, it is possible to identify holograms, which in this case leave no haptic impression, on the sheet obtained from the process of the invention.

Example 1

10

A commercial polyurethane acrylate made from long-chain polyesterdiol, aliphatic diisocyanate and terminal acrylic groups (molecular weight approximately 1500, functionality 2) is mixed with 20% hexanediol bisacrylate. This gives a liquid with a high viscosity of about 10 Pa*s. This liquid is used to prepare:

15

- a black paste A by grinding with 12% of carbon black FCF (average particle diameter 23 μm) on a triple-roll mill, and
- a white paste B by grinding 45% of an Al and Si stabilized rutile pigment (TiO_2 content 90%, density 3.9 g/cm^3).

20

Paste A is coated in a thickness of 10 μm onto a 50 μm thick, biaxially oriented and embossed polyester sheet and cured under inert gas by means of an electron beam 350 keV with a dose of 80 kGy.

- 25 Atop this there is applied a white paste B with a thickness of 50 μm , and curing is again carried out under inert gas with the electron beam, with a dose of 3 Mrad.

This product is coated with a pressure-sensitive adhesive in accordance with DE-OS 15 69 898, so that after drying the film has a thickness of 20 μm . The pressure-sensitive adhesive is lined with commercial release paper.

30

Subsequently, the polyester sheet is removed so that the embossed and otherwise mirror-smooth black surface of the product appears.

- 35 This surface is capable of rapid marking with a bar code, for example, using a controllable outlet laser. The contrast is so high that the code can be read without error using an evaluation device from a distance of 1 m.

Heating of the material at 200°C for 1 hour results in shrinkage of less than 1% in the lengthwise and transverse directions. Immersion in water and/or weathering in a Weatherometer for 500 h results in no adverse effects.

Claims

1. Process for producing a sheet, in which first of all a support foil is embossed by means of an embossing tool, the embossing tool having holographic structures, and then a sheet is produced on the embossed support foil so that at least one hologram is produced on the sheet.
2. Process according to Claim 1, characterized in that the support foil consists of a permanently embossed thermoset or thermoplastic material.
3. Process according to Claims 1 and 2, characterized in that the support foil consists of polyester or polyamide.
4. Process according to Claims 1 to 3, characterized in that the sheet is extruded, coated or cast onto the support foil.
5. Process according to Claims 1 to 4, characterized in that the sheet consists of a coating film which in particular is subsequently subjected to electron beam curing.
6. Process according to Claim 5, characterized in that the coating film has a thickness of from 0.5 to 30 μm , in particular from 5 to 15 μm .
7. Process according to Claims 1 to 6, characterized in that an additional adhesive layer of from 5 to 70 μm in thickness is arranged on the sheet and, if required, a release paper is arranged on this adhesive layer.
8. Sheet obtainable by a process according to at least one of the preceding claims.

Abstract

Process for producing a sheet, in which first of all a support foil is embossed by means of an embossing tool, the embossing tool having holographic structures, and then a sheet is produced on the embossed support foil so that at least one hologram is produced on the sheet.




Figure 1

9




Figure 1

002020-15435450

10

B




Figure 2

002020-15436460